



JM401-A Non asbestos composite sheet

Area of Applications: 无石棉缸头垫材料, 可密封各类润滑油、燃油等等介质。Non-asbestos Cylinder Head Facing (CHF) applications. Good for sealing all sorts of lubrication oils, fuels and combustion engine related medium.

Characteristics: Environmental friendly material, Elastomeric binders, with good corrosion resistance, heat insulation and sound insulation properties.

Temperature Recommended ≤ 350 °C

Thickness: 1.0-2.0mm

Other thickness can be supplied upon requested

技术参数 Specifications:

项 目 Properties	单 位 Unit	标准要求 Standards	检测依据 Test Method	
密度 Density	g/cm ³	2.3±0.3	ASTM F1315	
压缩率 (34.5MPa) Compressibility	%	≥ 10	ASTM F36	
回弹率 Recovery	%	≥ 35	ASTM F36	
Immersion 浸ASTM IRM903#油 (150±2°C@ 5 Hrs 小时)	重量变化 Weight change	%	≤ 30	ASTM F146
	厚度变化 Thick change	%	≤ 20	
Immersion 浸ASTM B号燃料油 (室温20-30 °C) ×5h	重量变化 Weight change	%	≤ 30	ASTM F146
	厚度变化 Thick change	%	≤ 20	